



Address: De Bruynestraat 53
 2597RE, The Hague, The Netherlands
 Tel: +31 627 544 756
 Email info@emamou.com
 Website: <http://emamou.com>

BIOPLASTIC GRANULES AND APPLICATIONS

	Colour	Original Compound	Applications
EBM.01	light yellow	PBAT 100%	<i>flexible packaging films (blown extrusion or cast processes)</i>
EBM.02	pink	PBAT 100% & Additives	<i>flexible films (blown extrusion)</i>
EBM.03	opaque white	PBAT 85% + mineral 15%	injection moulding and sheet extrusion/thermoforming applications
EBM.04	dark caramel	PBAT 80% + starch 20%	blown films
EBM.05	silk yellow	PBAT 78%, PLA 17%	<i>blown films (shopping bags, garbage bags, T-shirt bags, roll bags, and die-cut bags)</i>
EBM.06	light caramel	PBAT 50%, PLA 30%, starch 20%	blown films
EBM.07	dark opaque	PBAT.PLA.CaCO3	<i>blown films (roll bag, compost bag, heavy weight shopping bag, etc.)</i>
EBM.08	light white	PBS 100%, 1	<i>houseware appliances, electronic devices, decoration items (fishing net, fishing strings, fabrics, rope, sheet, containers, paper coating)</i>
EBM.09	opaque	PBS 100%, 2	<i>houseware appliances, electronic devices, decoration items (mono-filament, multi-filaments, T-die sheet, fishing net, fishing strings, fabrics, rope, sheet, containers, paper coating)</i>
EBM.10	milky colour	PBST 99-100%	<i>blown films (roll bag, compost bag, heavy duty bag)</i>
EBM.11	white	PLA 95%	<i>3D filament and injection molding applications</i>
EBM.12	opaque white	PLA 85%	<i>injection molding applications (cutlery (knives, forks, spoons), cup, box, tray, and baby toys)</i>
EBM.13	silk opaque	PLA 69%, PBAT 25%	<i>injection molding applications (straw with different thickness, bend or straight straw)</i>
EBM.14	light caramel	PLA 80%, PBAT 20%	blown films
EBM.15	opaque white	PLA 75%, Mineral 25%	injection molding applications
EBM.16	dark caramel	PE 60%, Starch 40%	blown films